


CATGUT

CHROM



Type	Twisted multifilament with a monofilament appearance
Composition	Strands of purified collagen taken from the serosal layer of selected bovines, tanned with chrome salts. Origin from BSE-free classified countries.
Coating	None
Colour	Dark brown
Tissue reaction	Moderate
Absorption	By phagocytosis. The rate of absorption is slowed down by chromizing. Complete mass absorption in approximately 90 days. Approximately 50% of tensile strength remain after 14 days. When used in infected tissues or in tissues with increased levels of proteolytic enzymes (stomach, cervix, vagina) it is more quickly absorbed.
Presentation	Box with 12 sutures; Cassette



*For quality
&
safety*

smi

www.sutures.be

Catgut Chrome
Revision 7

CATGUT
CHROM

CATGUT

CHROM

CHARACTERISTICS

- ☒ High tensile strength
- ☒ Absorption by phagocytosis
- ☒ Twisted structure
- ☒ Uniform diameter by centerless polishing (monofilament appearance)
- ☒ Hermetically sealed packing


BENEFITS

- Excellent tissue support
- Uniform absorption
- Excellent handling properties
- High flexibility
- High tensile strength
- Excellent knot security
- Soft passage through the tissues without sawing, tissue drag and trauma
- Excellent knot tie down
- Guaranteed seal and product sterility

INDICATIONS General soft tissue closing and/or ligation
especially in General surgery
Gastrointestinal surgery
Gynaecology
Obstetrics
Urology
Ophthalmic surgery

CONTRAINDICATIONS Cardiovascular surgery
Neurosurgery
Being absorbable not to use when an extended wound support is required.
Caution in patients with delayed wound healing (e.g. compromised immune system).
In the region of infected wounds
Known sensitivities or allergies to collagen or chromium

TENSILE STRENGTH



ABSORPTION

